

PRODUCT DATA

3 03 39 00 **Concrete
Curing**

KURE-N-SEAL

**Waterborne acrylic curing, sealing,
and dustproofing compound****Description**

Kure-N-Seal™ is a modified-acrylic-based liquid polymer. Kure-N-Seal™ is recommended for use on new or existing concrete floors as classified in ACI Guide 302, Table 1.1.

Yield

Curing only:

200 – 400 ft²/gallon (4.9 – 9.8 m²/L)

Second coat:

400 – 600 ft²/gallon (9.8 – 14.7 m²/L)
(dustproofing and sealing)

Renovating, dustproofing and sealing:

200 – 300 ft²/gallon (4.9 – 7.4 m²/L)

Under mastic-type floor adhesives:

400 – 600 ft²/gallon (9.8 – 14.7 m²/L)

Coverage varies with application method, texture and porosity of surface.

Packaging

5 gallon (18.9 L) pails

55 gallon (208 L) drums

Color

Milky white; dries clear

Shelf Life

1 year when properly stored

Storage

Store in unopened containers in a clean, dry area between 40 and 85° F (4 and 29° C). Keep from freezing.

Features

- Ensures high curing efficiency
- Reduces surface absorption of concrete
- Cures, seals and dustproofs
- Retains the moisture in concrete
- VOC compliant
- Compatible with a variety of carpet and tile adhesives

Benefits

- Concrete attains its full strength potential
- Makes surfaces easier to clean and maintain
- Economical
- Minimizes shrinkage cracking
- Meets EPA regulations; environmentally friendly
- Can be carpeted or tiled over

Where to Use

APPLICATION

- Curing freshly placed and finished concrete floors
- Sealing and dustproofing existing concrete

LOCATION

- Vertical and horizontal surfaces
- Interior or exterior

SUBSTRATE

- Smooth and textured concrete
- Precast concrete
- Paving stones
- Exposed aggregate
- Terrazzo

How to Apply**Surface Preparation**

1. Freshly placed concrete must be properly finished. The surface is application ready when it is damp but not wet and when it cannot be marred by foot traffic.
2. Existing concrete surfaces should be thoroughly repaired and cleaned before application. Surface must be clean, dry and free of dust, oil, grease, sealers and all other surface contaminants that might inhibit proper bond of material.

Application

1. Thoroughly mix material in original container before applying.
2. Apply material to form a continuous, uniform film by sprayer, roller, or brush.
3. For curing, only 1 application is necessary. Apply evenly and uniformly as soon as possible after final finishing.

NOTE: two coats are required under hot and windy weather conditions.

4. To seal and dustproof, two coats are required. Apply the second application when all trades are completed and site is ready for occupancy.

Technical Data

Composition

Kure-N-Seal™ is a modified-acrylic-based liquid polymer.

Compliances

- Recommended for use on concrete floors as classified in Table 1.1, ACI Guide 302
- ASTM C 309, Type 1, Class A and B
- AASHTO M-148
- Corps of Engineers CRD-C-304, Type 1, Class A and B
- USDA compliant for use in meat and poultry areas

Typical Properties

PROPERTY	VALUE
Solids, %, by weight	18

Test Data

PROPERTY	RESULTS	TEST METHODS
Moisture retention test , kg/m ² , at 200 ft ² /gal (5 m ² /L) (ASTM C 390 requirement)		ASTM C 156
Kure-N-Seal™	< 0.38	
Test requirement not to exceed	< 0.55	

Test results are averages obtained under laboratory conditions. Expect reasonable variations.

5. Do not over-apply or soak concrete surfaces with the curing compound. Do not allow the curing compound to pool on the surface. Over-application can result in alligatoring and mud cracking, whereby a film forms on the substrate before the material dries properly. Over-application may also cause opacity, as elements of the curing compound become trapped in the subsurface and cannot escape.

Drying Time

Times are based upon temperatures of 65 to 85° F (18 to 29° C) and 50% relative humidity.

Light foot traffic or between coats: 4 hours

Normal traffic: overnight

Maximum hardness: 7 days

Material will take longer to dry at either higher humidity or lower temperatures.

Clean Up

Clean tools immediately after use with soap and warm water.

For Best Performance

- For curing only, 1 coat may be sufficient; 2 coats, however, will give best results. To seal and dustproof, 2 coats are required.
- Not recommended for use in colored dry-shake applications
- Keep from freezing.
- DO NOT apply when concrete surfaces or ambient temperatures are below 40° F (4° C).
- Do not apply when surface temperature is above 120° F (49° C).
- Not recommended as a release agent.
- Do not apply to the interfacing of channels to be caulked with elastomeric sealants. Mask channels to avoid sealant-adhesion problems.
- Can be applied to natural or colored concrete, but mottling or ambering may occur.
- May highlight features and imperfections of the concrete surface.
- Concrete substrate must be fully dry before exposure to water or it may whiten.
- Although Kure-N-Seal™ is compatible with a variety of carpet, vinyl-tile and floor-covering adhesives, always conduct a test application before applying.
- Not intended for surfaces to receive concrete overlays or additional toppings, coatings, sealers or ceramic tile (without proper surface preparation).
- Kure-N-Seal™ is considered a light-duty floor sealer; it may rubber burn when subjected to forklift or other wheeled traffic.
- If Kure-N-Seal™ will be applied in or near areas containing foodstuffs, they should be removed before application.
- Only mechanical methods of removal are recommended.
- The small amount of solvent vapors released by Kure-N-Seal™ may be objectionable to people unaccustomed to the odor; do not apply Kure-N-Seal™ in or around buildings occupied by nonconstruction personnel without consulting building management.
- Make certain the most current versions of product data sheet and MSDS are being used; call Customer Service (1-800-433-9517) to verify the most current versions.
- Proper application is the responsibility of the user. Field visits by BASF personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

Health and Safety

KURE-N-SEAL™

Caution

Kure-N-Seal™ contains Solvent naphtha (petroleum), light aromatic, 1, 2, 4 trimethylbenzene.

Risks

Combustible liquid and vapor. May cause skin, eye or respiratory irritation. May cause dermatitis and allergic responses. Inhalation of vapors may cause irritation and intoxication with headaches, dizziness and nausea. Ingestion may cause irritation of mouth, throat and stomach with nausea and abdominal pain. Reports associate repeated or prolonged occupational overexposure to solvents with permanent brain, nervous system, liver and kidney damage. INTENTIONAL MISUSE BY DELIBERATELY INHALING THE CONTENTS MAY BE HARMFUL OR FATAL.

Precautions

READ MATERIAL SAFETY DATA SHEETS (MSDS) AND TECHNICAL DATA GUIDE BEFORE USING. DO NOT USE UNTIL ALL BYSTANDERS HAVE BEEN WARNED OF PRODUCT HAZARDS. KEEP AWAY FROM HEAT, FLAME AND SOURCES OF IGNITION. KEEP OUT OF THE REACH OF CHILDREN. Vapors are heavier than air. DO NOT cut or weld on or near empty container. Empty container may contain explosive vapors or hazardous residues. Keep container closed. Use only with adequate ventilation. Prevent contact with eyes, skin and clothing. Wash thoroughly after handling. DO NOT breathe vapors. DO NOT take internally. Use impervious gloves, eye protection and if the TLV is exceeded or product is used in a poorly ventilated area, use NIOSH/MSHA approved respiratory protection in accordance with applicable federal, state and local regulations. All label warnings must be observed until container is commercially cleaned or reconditioned.

First Aid

In case of eye contact, flush thoroughly with water for at least 15 minutes. SEEK IMMEDIATE MEDICAL ATTENTION. In case of skin contact, wash affected areas with soap and water. If irritation persists, SEEK MEDICAL ATTENTION. Remove and wash contaminated clothing. If inhalation causes physical discomfort, remove to fresh air. If discomfort persists, or any breathing difficulty occurs, or if swallowed, SEEK IMMEDIATE MEDICAL ATTENTION.

Refer to Material Safety Data Sheet (MSDS) for further information.

Proposition 65

This product contains materials listed by the state of California as known to cause cancer, birth defects, or other reproductive harm.

VOC Content

2.59 lbs/gal or 311 g/L, less water and exempt solvents.

**For medical emergencies only,
call ChemTrec (1-800-424-9300).**

**BASF Construction Chemicals, LLC –
Building Systems**

889 Valley Park Drive
Shakopee, MN, 55379

www.BuildingSystems.BASF.com

Customer Service 800-433-9517
Technical Service 800-243-6739



LIMITED WARRANTY NOTICE Every reasonable effort is made to apply BASF exacting standards both in the manufacture of our products and in the information which we issue concerning these products and their use. We warrant our products to be of good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, **BASF MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS,** and BASF shall have no other liability with respect thereto. Any claim regarding product defect must be received in writing within one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the BASF Technical Manager.

This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, BASF disclaims all **CONDITIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, BASF SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND.** BASF reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein should be verified by testing and carried out only by qualified experts. It is the sole responsibility of the customer to carry out and arrange for any such testing. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.

For professional use only. Not for sale to or use by the general public.

Form No. 1019388 9/07

Printed on recycled paper including 10% post-consumer fiber.

© 2007 BASF
Printed in U.S.A.