

## PRODUCT DATA

**3** 03 01 00 **Maintenance of  
Concrete****WATERPLUG®****One-component, cement-based,  
fast-setting water-stop repair mortar****Description**

Waterplug® is a one-component, quick-setting, Portland-cement-based hydraulic repair mortar that instantly stops running water through holes or cracks in concrete or masonry. It expands as it sets to lock into place even under constant water pressure.

**Yield**

Volume:  
15.6 in<sup>3</sup>/1 lb (254 cm<sup>3</sup>/0.45 kg)

Static cracks:  
3/4 by 3/4 by 28"/1 lb  
(1.9 by 1.9 by 70 cm/0.45 kg).

**Packaging**

2-1/2 lb (1.13 kg) cans  
10 lb (4.5 kg) cans  
50 lb (22.7 kg) pails

**Color**

Dark Gray

**Shelf Life**

1 year when properly stored

**Storage and Transportation**

Transport and store in unopened container in a cool, clean, dry area between 45 and 90° F (7 and 32° C). Keep container tightly sealed after opening to maintain shelf life freshness of unused portion of the remaining powder.

**Features**

- Fast setting
- Fully hydraulic
- Shrinkage compensated
- One component
- Ready to topcoat in 15 minutes with appropriate product
- Durable nonmetallic, nongypsum formula
- Waterplug® H formulation available for cold-weather applications

**Benefits**

- Stops running water; develops high strength quickly
- Sets above or below water
- Expands to lock in place
- Mixes easily with water only
- Minimizes downtime
- Maintains volume stability over time
- Use in all seasons and climates

**Where to Use**

## APPLICATION

- Nonmoving (static) cracks and holes with running water or moisture seepage
- For immersion service
- For anchoring vertical bolts
- Basements
- Foundations
- Retaining walls
- Sewers

## LOCATION

- Vertical, overhead, or horizontal
- Interior or exterior
- Above or below grade

## SUBSTRATE

- Concrete and masonry

**How to Apply****Mixing**

1. Mix Waterplug® powder with clean, potable water.
2. Use powder neat without adding any aggregates, chemical additives, or admixtures.
3. Add just enough water to mix rapidly by hand to a stiff, low-slump, putty consistency. Mix no longer than 30 seconds.
4. Mix only enough Waterplug® that can be successfully placed within 3 minutes under normal conditions (see Temperature). Do not retemper material after initially mixing.
5. Clean mixing vessel and tools immediately after each use.

## Technical Data

### Composition

Waterplug® is a proprietary mix composed of cement, graded silica, calcium hydroxide, fillers, and additives.

### Test Data

PROPERTY	RESULTS	TEST METHODS
<b>Compressive strength, psi (MPa)</b>		ASTM C 109
20 min – 120 min	1,800 (12.4)	
1 day	4,000 (27.6)	
7 days	5,000 (34.5)	
28 days	5,500 (37.9)	
<b>Tensile strength, psi (MPa)</b>		ASTM C 190
7 days	300 (2.1)	
28 days	350 (2.4)	
<b>Flexural strength, psi (MPa)</b>		ASTM C 348
7 days	600 (4.1)	
28 days	1,500 (10.3)	

Test results are averages obtained under laboratory conditions at 70° F (21° C) and 50% rh. Reasonable variations can be expected.

### Temperature

Cold or hot air, surface, and material temperatures will retard or quicken Waterplug® setting time.

Special attention must be given when both mixing and applying. The Waterplug® and mixing water should feel neutral to the touch, normally 70° F (21° C). On average Waterplug® will set in approximately 3 – 5 minutes.

#### HOT WEATHER USE

- From 86 to 100° F (30 to 37° C), Waterplug® will set very quickly. Material temperature should not be above 80° F (26° C) and mixing water over 100° F (37° C); otherwise set begins immediately and structural strength lessens when applying during these extreme conditions.
- Waterplug® should always be placed within 30 – 60 seconds after mixing.
- If appropriate, use ice water when mixing to slow down the setting action.

#### COLD WEATHER USE

- Waterplug® should be stored at or brought up to normal room temperatures, 40 to 70° F (4 to 21° C), before mixing and use. Do not apply Waterplug® if the ambient air or surface temperatures are 40° F (4° C) or less or are expected to fall below 40° F (4° C) within 12 hours after initial placement.
- For quicker set times at normal temperatures or applications down to 40° F (4° C), Waterplug® H may be used.

### Application

- Place Waterplug® with minimum working, kneading, or rubbing.
- Force Waterplug® repair mortar into cracks or holes and hold in place (without twisting) until set is fully achieved.
- Just prior to final hard set, Waterplug® may be "shaved" with a trowel until flush with the surrounding surface. Always shave from the center out, in the direction of the bond line.
- If the repair area is dry at the time of placement, keep substrate damp for 15 minutes minimum, using a fine spray misting of water, before and after placement.


#### SEALING JUNCTIONS

- To seal static cracks at the junction of floors and walls, rout or cut out the crack at least 3/4" (19 mm) wide and deep, slightly undercutting if possible.
- Flush away all loose debris, dust, and dirt with clean water.

- Force Waterplug® into the prepared crack with a round tool or margin trowel until a set is fully achieved and smooth out to form a cove at wall-to-floor junctions.
- Keep damp for at least 15 minutes.

#### STOPPING RUNNING WATER

- To stop active water from running through concrete and masonry, cut out crack or hole to a minimum depth and width of 3/4" (19 mm). Always square cut or undercut when possible; do not "V" cut.
- Start at top and force Waterplug® into crack. In areas of great pressure, do not place Waterplug® into opening immediately. Hold Waterplug® in hand or on trowel until a slight warming occurs. Then press Waterplug® firmly into opening.
- Do not remove trowel or hand pressure too soon so as to provide some confinement to Waterplug expansion during its set. Do not twist Waterplug® during placement or disturb during set time (5 minutes).
- After placement to stop the active water flow, carefully cut and "trowel shave" the patch level with the surrounding surface.



V-cut (wrong)

Square cut

Undercut (Best cut)

#### SEALING LEAKS IN JOINTS AND CRACKS

1. To stop leaking mortar joints or static cracks in below-grade masonry and concrete walls, cut out defective mortar joints or cracks to a minimum width and depth of 3/4" (19 mm). Undercut when possible.
2. Force Waterplug® into opening and keep damp for at least 15 minutes or until a set is fully achieved.

#### REPAIRING CONSTRUCTION FAULTS

1. For patching holes and voids, etc., in concrete walls, remove all tie wires and wood or steel separators by cutting back from surface to a minimum depth of 3/4" (19 mm).
2. When there is no active water present, repair mortars may be used more appropriately.

#### ANCHORING HARDWARE

1. To anchor steel bolts or posts in vertical concrete or masonry, drill a hole deep enough to properly secure bolt or post and large enough so there is at least 1/2" (13 mm) on all sides of bolt or post.
2. Fill hole with Waterplug® and tamp so that entire hole is full. Immediately center bolt or post over hole and force into the putty-like Waterplug®.
3. Tamp Waterplug® firmly around bolt or post; keep continuously moist for 15 minutes.
4. Apply no pressure or stress to bolt or post for a minimum of 5 hours after placement.

#### TOPCOATING

1. Cured Waterplug® repairs can be topcoated with Thoroseal® or Thoroseal® Plaster Mix (see Form Nos. 1019906 and 1019908), both modified with Acryl 60® (see Form No. 1019073), as soon as an initial set is reached.
2. Cured Waterplug® repairs can also be topcoated with various alkali-resistant acrylic coatings or used in conjunction with Thorocoat®, Thorocoat® 200 and Thorosheen® (see Form Nos. 1019100, 1019101, and 1019910).
3. Waterplug® may also be used with preformed waterproof sheet membranes after approximately 6 – 7 days cure.

#### Clean Up

Clean tools and equipment immediately with water. Cured material must be removed mechanically.

#### For Best Performance

- Do not apply to frozen or frost-covered surfaces.
- Do not apply to dynamic (moving) cracks.
- Do not use to fill expansion joints or control joints.
- Do not remix (retemper) hardened material.
- Do not use as a surface-applied coating or as a parging material.
- Do not fill voids greater than 30 in<sup>3</sup> (490 cm<sup>3</sup>) in a single lift.
- Do not use if hard lumps have developed in the powder.
- Make certain the most current versions of product data sheet and MSDS are being used; call Customer Service (1-800-433-9517) to verify the most current version.
- Proper application is the responsibility of the user. Field visits by BASF personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

#### Health and Safety

##### WATERPLUG®

##### Warning

Waterplug® contains Alumina cement; Silica, crystalline quartz; Portland cement; Iron oxide; Calcium hydroxide; Limestone; Anhydrite.

##### Risks

Product is alkaline on contact with water and may cause injury to skin or eyes. Ingestion or inhalation of dust may cause irritation. Contains small amount of free respirable quartz which has been listed as a suspected human carcinogen by NTP and IARC. Repeated or prolonged overexposure to free respirable quartz may cause silicosis or other serious and delayed lung injury.

#### Precautions

Avoid contact with skin, eyes and clothing. Prevent inhalation of dust. Wash thoroughly after handling. Keep container closed when not in use. DO NOT take internally. Use only with adequate ventilation. Use impervious gloves, eye protection and if the TLV is exceeded or used in a poorly ventilated area, use NIOSH/MSHA approved respiratory protection in accordance with applicable Federal, state and local regulations.

#### First Aid

In case of eye contact, flush thoroughly with water for at least 15 minutes. In case of skin contact, wash affected areas with soap and water. If irritation persists, SEEK MEDICAL ATTENTION. Remove and wash contaminated clothing. If inhalation causes physical discomfort, remove to fresh air. If discomfort persists or any breathing difficulty occurs or if swallowed, SEEK IMMEDIATE MEDICAL ATTENTION.

Refer to Material Safety Data Sheet (MSDS) for further information.

#### Proposition 65

This product contains material listed by the State of California as known to cause cancer, birth defects or other reproductive harm.

#### VOC Content

0 g/L or 0 lbs/gal less water and exempt solvents.

**For medical emergencies only,  
call ChemTrec (1-800-424-9300).**

**BASF Construction Chemicals, LLC –  
Building Systems**

889 Valley Park Drive  
Shakopee, MN, 55379

[www.BuildingSystems.BASF.com](http://www.BuildingSystems.BASF.com)

**Customer Service** 800-433-9517  
**Technical Service** 800-243-6739



**LIMITED WARRANTY NOTICE** Every reasonable effort is made to apply BASF exacting standards both in the manufacture of our products and in the information which we issue concerning these products and their use. We warrant our products to be of good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, **BASF MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS,** and BASF shall have no other liability with respect thereto. Any claim regarding product defect must be received in writing within one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the BASF Technical Manager.

This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, BASF disclaims all **CONDITIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. BASF SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND.** BASF reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein should be verified by testing and carried out only by qualified experts. It is the sole responsibility of the customer to carry out and arrange for any such testing. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.

**For professional use only. Not for sale to or use by the general public.**

Form No. 1019124 8/07

Printed on recycled paper including 10% post-consumer fiber.

© 2007 BASF

Printed in U.S.A.