



# Planitop<sup>®</sup> X

**One-Component, Fast-Setting, Fiber-Reinforced, Vertical and Overhead Repair Mortar**



## DESCRIPTION

*Planitop X* is a one-component, fiber-reinforced, shrinkage-compensated, high-early-strength, fast-setting, polymer-modified, high-build cementitious repair mortar with a corrosion inhibitor.

## WHERE TO USE

- Interior/exterior
- Vertical/overhead
- Precast concrete elements
- Columns
- Joint repair of concrete walls

## FEATURES AND BENEFITS

- Can be mixed with water or *Planicrete<sup>®</sup> AC*
- Can be shaved to match the surrounding contour
- 1/16" to 4" (1,5 mm to 10 cm) vertical thickness
- 1/16" to 2" (1,5 mm to 5 cm) overhead thickness
- Contains corrosion inhibitor
- Shrinkage-compensated

## INDUSTRY STANDARDS AND APPROVALS

- ASTM: Meets or exceeds the requirements of ASTM C928, R2

LEED v4 Points Contribution

LEED Points

Health Product Declaration (HPD)\* .....Up to 2 points

\* Using this product may help contribute to LEED certification of projects in the category shown above. Points are awarded based on contributions of all project materials.

## SURFACE PREPARATION

- Concrete surface must be clean and free of loose particles, efflorescence, paint, tars, grease, asphaltic materials, bond breakers, curing compounds, wax and any foreign substance.
- Mechanically profile clean, sound and stable concrete surfaces to obtain a concrete surface profile (CSP) equal to or greater than #5 per ICRI Guideline #310.2R-2013.

## MIXING

Before product use, take appropriate safety precautions. Refer to the Safety Data Sheet for details.

1. Into a clean mixing container, pour 3/4 of the required 0.8 U.S. qt. (0,76 L) of potable water per 10-lb. (4,54-kg) bag, or 3/4 of the required 1 U.S. gal. (3,79 L) of potable water per 50-lb. (22,7-kg) bag or pail.  
Note: If *Planicrete AC* is being used, replace the full amount of required water with diluted *Planicrete AC* per its Technical Data Sheet.
2. Slowly add the full bag of *Planitop X* into the mixing container while mixing with a drill and Jiffy mixer.
3. Add as much of the remaining 1/4 of fluid as needed.
4. Mix for 3 to 4 minutes. Continue to mix until a smooth, homogenous consistency is achieved.

## APPLICATION

Read all installation instructions thoroughly before installation.

1. Before application, ensure that prepared concrete is saturated surface-dry (SSD).
2. Apply a scrubcoat of *Planitop X*.



- Apply *Planitop X* directly to the scrubcoat before it dries out.
- Apply *Planitop X* by float, working from the center of the repair to the outer edge. Finish the application similar to the surrounding concrete.

## CURING

- Protect *Planitop X* from high wind or direct sunlight during curing.
- Protect the surface with wet burlap or a continuous mist spray for at least 4 to 6 hours after placement.
- Alternatively, immediately after finishing, apply a water-based curing compound conforming to ASTM C309.

## CLEANUP

- Immediately clean tools and equipment with water before the material hardens. Hardened material must be mechanically removed.

## LIMITATIONS

- Do not apply over substrates containing asbestos.
- Do not mix more material than can be installed within the working time.
- Use at between 55°F and 85°F (13°C and 29°C).
- Utilize ACI cold-weather or hot-weather guidelines when required.
- Do not overmix or overwork *Planitop X*.
- Other than MAPEI's *Planicrete AC* latex admixture, do not add any other cements, aggregates or materials to *Planitop X*.

### Product Performance Properties at 72°F (22°C)

Laboratory Tests	Results
Compressive strength – ASTM C109 (CAN/CSA-A5)	
3 hours	> 2,900 psi (20 MPa)
1 day	> 5,075 psi (35 MPa)
7 days	> 5,800 psi (40 MPa)
28 days	> 6,600 psi (45,5 MPa)

Bond strength – ASTM C882 (modified)	
1 day	> 1,400 psi (9,66 MPa)
28 days	> 1,800 psi (12,4 MPa)
Length change – ASTM C157 (modified C928)	
28 days, water-cured	< +0.15%
28 days, air-cured	< -0.15%
Flexural strength – ASTM C348 (CAN/CSA-A23.3-8C)	
1 day	> 580 psi (4 MPa)
7 days	> 725 psi (5 MPa)
28 days	> 870 psi (6 MPa)
VOCs (Rule #1168 of California's SCAQMD)	0 g per L

### Shelf Life and Application Properties at 73°F (23°C) and 50% relative humidity

Mortar consistency	Plastic
Working time	5 to 6 minutes
Initial set	> 6 minutes
Final set	< 25 minutes
Shelf life	1 year when stored in original, unopened packaging

### Packaging and Approximate Coverage\*

Size	Yield
Bag: 10 lbs. (4,54 kg)	0.09 cu. ft. (0,0025 m <sup>3</sup> )
Bag: 50 lbs. (22,7 kg)	0.46 cu. ft. (0,013 m <sup>3</sup> )
Pail: 50 lbs. (22,7 kg)	0.46 cu. ft. (0,013 m <sup>3</sup> )

\* Coverage shown is for estimating purposes only. Actual jobsite coverage may vary according to substrate conditions and setting practices.

Refer to the SDS for specific data related to health and safety as well as product handling.

### LEGAL NOTICE

The contents of this Technical Data Sheet ("TDS") may be copied into another project-related document, but the resulting document shall not supplement or replace requirements per the TDS in effect at the time of the MAPEI product installation. For the most up-to-date TDS and warranty information, please visit our website at

[www.mapei.com](http://www.mapei.com). **ANY ALTERATIONS TO THE WORDING OR REQUIREMENTS CONTAINED IN OR DERIVED FROM THIS TDS SHALL VOID ALL RELATED MAPEI WARRANTIES.**

Before using, the user must determine the suitability of our products for the intended use, and the user alone assumes all risks and liability. **ANY CLAIM SHALL BE DEEMED WAIVED UNLESS MADE IN WRITING TO US WITHIN FIFTEEN (15) DAYS FROM DATE IT WAS, OR REASONABLY SHOULD HAVE BEEN, DISCOVERED.**

We proudly support the following industry organizations:



TTMAC ACTTM



aci  
American Concrete Institute®



ASC  
THE ADHESIVE AND SEALANT COUNCIL  
SUSTAINING THE FUTURE



**MAPEI Headquarters of North America**  
1144 East Newport Center Drive  
Deerfield Beach, Florida 33442  
1-888-US-MAPEI (1-888-876-2734) /  
(954) 246-8888

**Technical Services**  
1-888-365-0614 (U.S. and Puerto Rico)  
1-800-361-9309 (Canada)  
**Customer Service**  
1-800-42-MAPEI (1-800-426-2734)

**Services in Mexico**  
0-1-800-MX-MAPEI (0-1-800-696-2734)  
**Edition Date:** April 20, 2018  
PR: 4654 MKT: 18-1548

For the most current BEST-BACKED™ product data and warranty information, visit [www.mapei.com](http://www.mapei.com).

All Rights Reserved. Printed in the USA. © 2018 MAPEI Corporation.