

**Product Data Sheet**  
Edition 8.15.2006  
Identification no. C371  
Sikadur AnchorFix-2

# Sikadur<sup>®</sup> AnchorFix-2

## High-performance, epoxy acrylate, anchoring adhesive

<b>Description</b>	Sikadur AnchorFix-2 is a two-component, solvent- and styrene-free, modified-acrylic, anchoring adhesive.
<b>Where to Use</b>	As a fast-curing anchoring adhesive for all grades of rebars, threaded rods, bolts and special fastening systems. Install in concrete and masonry base materials.
<b>Advantages</b>	<ul style="list-style-type: none"> <li>■ Low sensitivity to mixing errors.</li> <li>■ Styrene-free, solvent-free</li> <li>■ Low waste.</li> <li>■ Can be dispensed/mixed with a standard, good quality caulking gun.</li> <li>■ Satisfies AC 58 creep criteria. Current ICC listing valid through 12/31/2007. Contact Sika's Technical Service Department for updated information at 1-800-933-7452.</li> </ul> <ul style="list-style-type: none"> <li>■ Fast-curing.</li> <li>■ Low odor.</li> <li>■ Moisture tolerant.</li> </ul>
<b>Packaging</b>	10 fl. oz. (300 ml) two-component collapsible "cartridge-in-cartridge" system. Ready-to-use with a standard, good quality caulking gun.

### Gel and Curing Times

Application Temperature	Gel Time	Cure Time
95°F (35°C)	2 minutes	25 minutes
86°F (30°C)	3 minutes	35 minutes
68°F (20°C)	5 minutes	40 minutes
50°F (10°C)	8 minutes	70 minutes
41°F (5°C)	12 minutes	90 minutes
32°F (0°C)	20 minutes	3 hours
23°F (-5°C)	50 minutes	15 hours
14°F (-10°C)	80 minutes	24 hours

### WARNING

**Component A: IRRITANT.** Contains epoxy resin, and silica quartz (sand). Eye irritant. May cause skin/respiratory irritation. Harmful if swallowed.

**Component B: IRRITANT, SENSITIZER.** Causes eye irritation. May cause skin/respiratory irritation. Prolonged and/or repeated skin contact may cause an allergic reaction/sensitization. Harmful if swallowed.

Cured material, if sanded, may result in exposure to a chemical known to the State of California to cause cancer.

### Technical Data

<b>Shelf Life</b>	Use within 12 months of manufacturing date.
<b>Storage Conditions</b>	Store in original unopened packaging in cool, well-ventilated conditions at 40°-80°F (4-7°) and out of direct sunlight.
<b>Color</b>	Component. A+B mixed: uniform gray
<b>Mixing Ratio</b>	Component A : Component B = 10:1 by volume
<b>Consistency</b>	Component. A+B mixed: non-sag, creamy paste
<b>Application Temperatures</b>	Substrate and ambient: 14°-86°F (-10°C-30°C)
<b>Density (Mixed)</b>	2.75 lb./gal (.33 kg/l)

Construction



**First Aid**

**Eyes:** Flush eyes with water for at least 15 minutes **Skin:** Immediately flush skin and water for at least 15 minutes. **Ingestion:** Do not induce vomiting. Contact a physician. **Inhalation:** Remove to fresh air. Contact a physician if symptoms persist. **Contact a physician immediately with all cases if symptoms persist.**

**Handling and Storage**

Avoid direct contact with skin and eyes. Use chemical resistant gloves/goggles/clothing. Use with adequate general and local exhaust ventilation. In the absence of adequate ventilation, use a properly fitted NIOSH approved respirator. Wash hands thoroughly after handling product. Remove contaminated clothing and launder before reuse. Uncured material can be removed with solvent. Strictly follow solvent manufacturer's warnings and instructions for use. Cured material can only be removed mechanically. Keep cartridge tightly closed.

**Clean Up**

In case of spill, wear chemical resistant gloves/goggles/clothing. Ventilate area. In absence of adequate ventilation, use a properly fitted NIOSH respirator. Contain spill and collect with absorbent material and transfer to a sealed container. Dispose of in accordance with applicable local, state and federal regulations.

Anchor Diameter (in.)	Drill Bit Diameter (in.)	Embedment Depth (in.)	Allowable Tensile Bond Strength Min. 2,000 psi (13.8 MPa) Concrete (lbs.)	Allowable Tensile Bond Strength Min. 4,000 psi (27.5 MPa) Concrete (lbs.)	Allowable Shear Load $\geq$ 2,000 psi (13.8 MPa) Concrete (lbs.)
3/8	7/16	2-1/4	1,155	1,680	335
		3-1/2	1,950	2,785	1,125
		4-1/2	2,310	3,360	1,125
1/2	9/16	3	1,720	2,500	600
		4-1/4	3,225	4,605	2,000
		6	3,435	5,010	2,000
5/8	3/4	3-3/4	2,855	4,160	940
		5	3,745	5,350	3,130
		7-1/2	5,715	8,320	3,130
3/4	7/8	4-1/2	4,540	6,610	1,350
		6-3/4	5,930	8,475	4,505
		9	8,050	11,520	4,505
1	1-1/8	6	6,735	7,610	2,400
		8-1/4	7,330	10,475	8,010
		12	10,635	15,225	8,010

**Load Capacities - Threaded Rod**

- 1) Allowable loads are based on a minimum safety factor of 3. Higher factors of safety may be warranted depending on actual application and job site conditions. Consult a design professional prior to use.
- 2) Minimum concrete base material thickness must be 1.5 times the anchor embedment depth.
- 3) Allowable load of adhesive anchor must be the lesser of bond or steel strength.

**\*\*For information on the effects of Anchor Spacing and Edge Distance on adhesive anchor performance, please contact Sika's Technical Service Department.**

Maximum Recommended Tightening Torque on Nut/Washer for Threaded Rod

**Note:** Maximum tightening torque applied to nut and washer recommended to prevent over-stress of adhesive.

	Threaded Rod Diameter (in.)						
	3/8	1/2	5/8	3/4	7/8	1	1-1/4
<b>Max. Tightening Torque (ft-lbf)</b>	15	30	60	110	125	150	250

Rebar Size (Diameter)	Drill Bit Diameter (in.)	Embedment Depth (in.)	Allowable Tensile Bond Strength Min. 2,000 psi (13.8 MPa) Concrete (lbs.)	Allowable Tensile Bond Strength Min. 4,000 psi (27.5 MPa) Concrete (lbs.)	Allowable Shear Load $\geq$ 2,000 psi (13.8 MPa) Concrete (lbs.)
No. 3 (3/8")	1/2	3-3/8	935	1,340	1,190
No. 4 (1/2")	5/8	4-1/2	1,685	2,410	1,970
No. 5 (5/8")	3/4	5-5/8	2,435	3,480	2,940
No. 6 (3/4")	7/8	6-3/4	3,185	4,550	4,110
No. 7 (7/8")	1	7-7/8	3,935	5,620	5,450
No. 8 (1")	1-1/8	9	4,680	6,690	7,030

**Load Capacities - Reinforcing Bar**












- 1) Allowable loads are based on a minimum safety factor of 4. Higher factors of safety may be warranted depending on actual application and job site conditions. Consult a design professional prior to use.
- 2) Minimum concrete base material thickness must be 1.5 times the anchor embedment depth.
- 3) Allowable load of adhesive anchor must be the lesser of bond or steel strength.

**\*\*For information on the effects of Anchor Spacing and Edge Distance on adhesive anchor performance, please contact Sika's Technical Service Department.**













**Methods of Use**

**Solid Base Material**

<p>1</p>  <p>Drill the hole to the correct diameter and depth using a rotary hammer drill.</p>	<p>2</p>  <p>Blow the hole clean with compressed air, brush clean with a nylon brush and blow clean again. Hole may be dry or damp but must be free from standing water.</p>	<p>3</p>  <p>Unscrew the cap.</p>	<p>4</p>  <p>Pull the red plug.</p>
<p>5</p>  <p>Cut the bags to remove the red plug</p>	<p>6</p>  <p>Attach the static mixing nozzle.</p>	<p>7</p>  <p>Insert the cartridge into the applicator gun. Dispense the first part of the extruded adhesive to waste until a uniform color is achieved.</p>	<p>8</p>  <p>Insert the mixer nozzle to the far end of the hole and half fill hole (depending upon application). Withdraw nozzle as you fill the hole. For deep holes extension tubing can be used.</p>
<p>9</p>  <p>Prior to use, remove surface contaminants such as oil or grease from anchor to avoid inadequate bond. Immediately insert the anchor hardware.</p>	<p>10</p>  <p>This should be done slowly with a slight twisting motion. Excess resin should be removed from the mouth of the hole before it sets. Use chemical resistant gloves.</p>	<p>11</p>  <p>Leave the anchor undisturbed until curing time has elapsed, then attach the fixture and tighten the nut.</p>	

**Hollow Base Material**

<p>1</p>  <p>Drill the hole to the correct diameter and depth. This can be done with either a hammer drill or rotary-only machine depending upon the substrate.</p>	<p>2</p>  <p>Blow the hole clean with compressed air, brush clean with a nylon brush and blow clean again. Hole may be dry or damp but must be free from standing water.</p>	<p>3</p>  <p>Insert the correct perforated screen.</p>	<p>4</p>  <p>Unscrew the cap.</p>	<p>5</p>  <p>Pull the red plug.</p>	<p>6</p>  <p>Cut the bags to remove the red plug.</p>
<p>6</p>  <p>Attach the static mixing nozzle.</p>	<p>7</p>  <p>Insert the cartridge into the applicator gun. Dispense the first part of the extruded adhesive to waste until a uniform color is achieved.</p>	<p>8</p>  <p>Insert mixer nozzle to the far end of the perforated sleeve and completely fill the sleeve with resin. Withdraw the mixer nozzle as the sleeve fills.</p>	<p>10</p>  <p>Prior to use, remove surface contaminants such as oil or grease from anchor to avoid inadequate bond. Immediately insert the anchoring hardware. This should be done slowly with a slight twisting motion. Leave the anchor undisturbed until the cure time has elapsed, then attach the fixture and tighten the nut.</p>		

Construction

**KEEP CONTAINER TIGHTLY CLOSED • KEEP OUT OF REACH OF CHILDREN • NOT FOR INTERNAL CONSUMPTION • FOR INDUSTRIAL USE ONLY**

All information provided by Sika Corporation ("Sika") concerning Sika products, including but not limited to, any recommendations and advice relating to the application and use of Sika products, is given in good faith based on Sika's current experience and knowledge of its products when properly stored, handled and applied under normal conditions in accordance with Sika's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of Sika's control are such that Sika assumes no liability for the provision of such information, advice, recommendations or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations or instructions related to its products. The user of the Sika product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application of the product(s). Sika reserves the right to change the properties of its products without notice. All sales of Sika product(s) are subject to its current terms and conditions of sale which are available at [www.sikacorp.com](http://www.sikacorp.com) or by calling 800-933-7452.

**Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Technical Data Sheet, product label and Material Safety Data Sheet which are available online at [www.sikaconstruction.com](http://www.sikaconstruction.com) or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Technical Data Sheet, product label and Material Safety Data Sheet prior to product use.**

Sika warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Technical Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKASHALL NOT BELIEABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKASHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Visit our website at [www.sikaconstruction.com](http://www.sikaconstruction.com)

1-800-933-SIKA NATIONWIDE

**Regional Information and Sales Centers.** For the location of your nearest Sika sales office, contact your regional center.

**Sika Corporation**  
201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: 800-933-7452  
Fax: 201-933-6225

**Sika Canada Inc.**  
601 Delmar Avenue  
Pointe Claire  
Quebec H9R 4A9  
Phone: 514-697-2610  
Fax: 514-694-2792

**Sika Mexicana S.A. de C.V.**  
Carretera Libre Celaya Km. 8.5  
Fracc. Industrial Balvanera  
Corregidora, Queretaro  
C.P. 76920  
Phone: 52 442 2385800  
Fax: 52 442 2250537



Sika and Sikadur are registered trademarks. Printed in USA.

