

Product Data Sheet

Edition 3.29.2011
 Identification no.
 Sikasil WS-290

A. R. Chambers Supply
111 Thirty-Fifth Street
Pittsburgh, PA 15201
412-681-8955

Sikasil® WS-290

Ultra low modulus, neutral cure silicone sealant

| | |
|----------------------------|---|
| Description | Sikasil WS-290 is a one-part, neutral-curing, ultra low-modulus, low to no bleed silicone sealant that cures to a durable, flexible building sealant. Sikasil WS-290 performs exceptionally well under dynamic conditions due to its ultra-low modulus, high extension/compression, recovery properties and strong adhesion to most building materials. Sikasil WS-290 accommodates long-term movement of +100-50% in properly designed joints and is particularly well suited for use in Exterior Insulation Finish Systems (EIFS). Meets the requirements of ASTM C-920, Type S, Grade NS, Class 100/50, Use NT, M, G, A, O; TT-S-00230C, Type II, Class A; TT-S-001543A, Class A; CAN/CGSB-1 9.1 3-M87, AAMA 808.3 |
| Where to Use | Sikasil WS-290 silicone sealant is designed primarily for sealing expansion and control joints in precast concrete panels, architectural stones, metal curtainwalls, perimeter sealing of doors and windows, Exterior Insulation Finish Systems (EIFS) and numerous other areas requiring a high-performance sealant. It adheres tenaciously to concrete, natural stones, masonry, steel, fluoropolymer painted and powder coated aluminum, wood, vinyl and many other plastics, generally without need for a primer, and performs equally well in new or remedial construction. |
| Packaging | 10.0 fl.oz. (.295 ml) plastic cartridges, 20 fl.oz. (.600 ml) sausages |
| How to Use | |
| Surface Preparation | The substrate must be clean, dry, frost free, sound and free of any oils, greases or incompatible sealers, paints or coatings that may interfere with adhesion. POROUS SUBSTRATES – clean by mechanical methods to expose a sound surface free of contamination and laitance. NON-POROUS SUBSTRATES – for cleaning non-porous substrates, use two rag wipe method using xylene or an approved commercial solvent. Allow solvent to evaporate prior to sealant application. |
| Priming | Sikasil WS-290 is designed to obtain adhesion without the use of a primer; however, certain substrates may require a primer. Test by applying the sealant and/or primer sealant combination to confirm results and proposed application methods. Refer to Technical Data Sheet for Sikasil Primer 2100 and contact Technical Service for additional information. |

Typical Data

| | |
|---------------------------|--|
| Shelf Life | 12 months in original unopened cartridges. |
| Storage Conditions | Store in unopened containers at temperatures lower than 80°F (27°C). |
| Colors | White, Colonial White, Aluminum, Limestone, Black, Bronze, Medium Bronze |
| VOC Content | 29 g/l |

Uncured Properties at 77°F (25°C), 50% R.H.

| | |
|---------------------------------|---|
| Tool Time (Initial Skin) | 30 minutes (higher temperatures and/or humidity will shorten this time) |
| Cure Time | 7-14 days |
| Flow, Sag, Slump | none |
| Full Adhesion | 7-14 days |
| Tack Free Time | 50 min. |

Cured Properties after 7 days at 77°F (25°C), 50% R.H.

| | |
|---|--------------------|
| Dynamic Movement Capability (ASTM C-719) | +100%, -50% |
| Elongation (ASTM D-412) | 1200% |
| Shore A Hardness (ASTM C-661) | 9 |
| Ozone/UV Resistance (weatherometer) | Excellent |
| Peel Strength (ASTM C-794) | 20-40 pli |
| Staining, Color Change | none |
| 100% Modulus (ASTM D-412) | 42 psi (0.29 MPa) |
| Service Temperature Range | -80°F to 350°F |
| Tensile Strength (ASTM D-412) | 165 psi (1.14 MPa) |



| | |
|--------------------------------|--|
| Application | <p>The number of joints and the joint width should be designed for a maximum of +100 and -50% movement of joint width at time of installation. The depth of the sealant should be 1/2 the width of the joint. The maximum depth is 1/2 inch (13mm) and the minimum is 1/4 inch (6mm). To control joint depth, use closed cell polyethylene, non-gassing polyolefin or open cell polyurethane backer rod. If joint depth does not allow for backer rod, use polyethylene bond breaker tape to prevent three-sided adhesion. Closed cell backer rod should be 25% larger than joint width; do not compress more than 40%. Open cell should be compressed 40%. Do not use open cell rod in horizontal on grade joint or with E.I.F.S. When installing during time of large temperature swings such as spring or fall, and in joints designed for movement greater than $\pm 25\%$, be aware of the significant joint movement before cure, may cause aesthetic issues such as ripples in the sealant surface. Performance will not be affected.</p> <p>Ready to use, apply using professional caulking gun. Do not open product container until preparation work has been completed. Apply sealant using consistent, positive pressure to force sealant into the joint. Tool sealant to create a concave joint shape and maximum adhesion. Dry tooling is recommended. DO NOT use soapy water or other liquids when tooling.</p> |
| Tooling & Finishing | <p>All joints should be masked to ensure a neat appearance and prevent sealant applied outside the joint. Place nozzle of the gun into bottom of joint and fill entire joint making complete contact with joint sides. Keep the nozzle in the sealant, continue with a steady flow of sealant preceding the nozzle to avoid air entrapment. Tool the sealant slightly concave using dry-tooling techniques. Do not tool with soap or detergent and water solutions.</p> |
| Limitations | <ul style="list-style-type: none"> ■ Do not allow sealant to come in contact with solvent during cure. ■ Do not allow sealant to come in contact with curing polyurethane sealants during cure. ■ Not intended for immersion. ■ Sealant may be applied below freezing temperatures if substrates are completely dry, frost free and clean. Contact Technical Service for more information. ■ Do not apply when substrate temperatures are below -20°F or above 130°F. ■ Not intended for structural glazing. ■ Not recommended for horizontal vehicular traffic. ■ Do not apply to surfaces that will be painted as sealant surface will not hold paint. ■ Do not apply to damp or wet substrates. ■ Lower temperature and humidity will extend tack free and cure rates. ■ Allow treated wood to age six months before application. ■ Brass and copper may be discolored. Test apply prior to application. ■ Test sensitive substrates, such as mirror backings, for compatibility before use. |
| CAUTION | <p>WARNING: IRRITANT, SENSITIZER. Contains Methyl ethyl ketoxime (CAS: 96-29-7), Oximino Silane (Trade Secret). Direct eye contact may cause irritation. Eye contact may cause conjunctivitis, corneal damage, or severe chemical burns. May cause skin irritation and sensitization. May be absorbed through the skin. May cause irritation to respiratory system. May cause drowsiness. Maybe harmful if swallowed. If heated, silicones can form formaldehyde vapors. Formaldehyde is a potential cancer hazard, a known skin and respiratory sensitizer, and an irritant to the eyes, nose, throat, skin, and digestive system. Product contains oximes, possible skin sensitizers.</p> |
| Handling and Storage | <p>Use with adequate ventilation. Product evolves Methyl ethyl ketoxime (MEKO) and methanol when exposed to water or humid air. Provide adequate ventilation to control MEKO within exposure guidelines. Keep container closed and store away from water or moisture or oxidizing materials.</p> |
| First Aid | <p>Remove to fresh air. Remove from skin and immediately flush with water for 15 minutes. Get medical attention if irritation develops or ill effects persist. Treat according to person's condition and specifics of exposure.</p> |
| Clean Up | <p>Observe personal protective equipment recommendations described in MSDS. Disposal of collected product, residues, and cleanup materials may be governmentally regulated. Observe all applicable local, state and federal waste management regulations. Wipe up and contain for disposal. Final cleaning may require use of steam, solvents, or detergents.</p> |

KEEP CONTAINER TIGHTLY CLOSED • KEEP OUT OF REACH OF CHILDREN • NOT FOR INTERNAL CONSUMPTION • FOR INDUSTRIAL USE ONLY

All information provided by Sika Corporation ("Sika") concerning Sika products, including but not limited to, any recommendations and advice relating to the application and use of Sika products, is given in good faith based on Sika's current experience and knowledge of its products when properly stored, handled and applied under normal conditions in accordance with Sika's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of Sika's control are such that Sika assumes no liability for the provision of such information, advice, recommendations or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations or instructions related to its products. The user of the Sika product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application of the product(s). Sika reserves the right to change the properties of its products without notice. All sales of Sika product(s) are subject to its current terms and conditions of sale which are available at www.sikacorp.com or by calling 800-933-7452.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Technical Data Sheet, product label and Material Safety Data Sheet which are available online at www.usa.sika.com or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Technical Data Sheet, product label and Material Safety Data Sheet prior to product use.

LIMITED WARRANTY: Sika warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Technical Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKASHALLNOTBELIABLEUNDERANYLEGALTHEORYFORSPECIALORCONSEQUENTIALDAMAGES. SIKASHALLNOTBERESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Visit our website at www.usa.sika.com

1-800-933-SIKA NATIONWIDE

Regional Information and Sales Centers. For the location of your nearest Sika sales office, contact your regional center.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 800-933-7452
Fax: 201-933-6225

Sika Canada Inc.
601 Delmar Avenue
Pointe Claire
Quebec H9R 4A9
Phone: 514-697-2610
Fax: 514-694-2792

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537

Sika and Sikasil are registered trademarks.
Made in USA. Printed in USA.

