



# DURALKOTE 240

## HIGH BUILD, FLEXIBLE EPOXY COATING

### DESCRIPTION

**DURALKOTE 240** is a two-component, 100% solids, high performance epoxy coating system designed for use on concrete floors and walls. DURALKOTE 240 is flexible, offers exceptional chemical and abrasion resistance, and provides excellent adhesion to properly prepared surfaces. DURALKOTE 240 produces a glossy, tile-like, easily maintained surface. DURALKOTE 240 is available in 4 standard colors, and in a Neutral Base that can be colored with EUCLID UNIVERSAL COLOR PACKS; available in 33 standard colors.

### PRIMARY APPLICATIONS

- Showrooms
- Warehouse floors
- Water treatment facilities
- Mechanical rooms
- Chemical processing and manufacturing plants
- Food service plants
- Truck/auto bay areas

### FEATURES/BENEFITS

- High build
- Chemical resistance
- Glossy, tile-like finish
- 33 colors available using color packs

### TECHNICAL INFORMATION

#### Material Properties @ 75°F (24°C)

Mixing Ratio (A:B, by volume)	1:1
VOC Content	≤ 50 g/L
Viscosity Mixed, cp	3,000 to 5,000
Pot Life full unit, minutes	15 to 25
Gel Time (100g sample), minutes	30 to 40
Tack Free Time 15 mils, hours	4 to 6
Hardness ASTM D2240, Shore D	75 to 85
Tensile Strength ASTM D638, psi (MPa)	1,800 to 2,000 (12.4 to 13.8)
Tensile Elongation ASTM D638, % at break	15 to 25

**Appearance:** DURALKOTE 240 standard colors are Light Gray, Tile Red, Tan, and White. DURALKOTE 240 is also available in a Neutral Base that can be colored using EUCLID UNIVERSAL COLOR PACKS, which are available in 33 standard colors. See the EUCLID UNIVERSAL COLOR CHART for available colors.

#### Chemical Resistance

<b>ACIDS</b>	
Acetic 10%	3D
Chromic 10%	2D
Citric 10%	3D
Formic 25%	1
Hydrochloric 10%	2D
Lactic 85%	2D
Nitric 10%	3D
Phosphoric 10%	3
85%	NR
Sulfuric Acid 10%	3D
50%	3D
98%	NR
Hydrofluoric 10%	2D
<b>SOLVENTS</b>	
Ethyl Alcohol 95%	1
Ethyl Acetate	NR
Methanol	1
Methyl Ethyl Ketone	NR
Mineral Spirits	4
Methylene Chloride	NR
Toluene	1
Xylene	1
Trichloroethane	2

#### ALKALIES/SALTS

Ammonia 29%	4
Potassium Hydroxide 50%	4
Sodium Hydroxide 50%	4
Detergent Solution	4
Ammonium Sulfate 50%	4
Sodium Chloride 50%	4
Ferric Chloride 50%	3D
Sodium Hypochlorite 10%	3D
Hydrogen Peroxide 35%	3D

#### MISCELLANEOUS

Brake Fluid	3
Skydrol	3
Formaldehyde 37%	3
Ethylene Glycol	4
Propylene Glycol	3
Vegetable Oil	4
Gasoline	2
Water	4
Anti Freeze	4
Bleach	4

1 = Incidental (8 hrs)  
 2 = Splash & spill (72 hrs)  
 3 = Extended exposure (7 days)  
 4 = Long term exposure (30 days)  
 D = Discoloration  
 NR = Not rated

### PACKAGING

DURALKOTE 240 standard colors are packaged in a 4 gal (15.2 L) case containing two 2 gal (7.6 L) kits. DURALKOTE 240 is also packaged in a Neutral Base & Color Pack kit that contains two 2 gal (7.6 L) kits of Neutral Base and two Universal Color Packs of the chosen color. Alternately, the DURALKOTE 240 Neutral Base 4 gal (15.2 L) case and Universal Color Packs are available separately.

### SHELF LIFE

2 years in original, unopened containers

### COVERAGE

Primer (optional)	ft <sup>2</sup> /gal (m <sup>2</sup> /L)	Neat Coating	ft <sup>2</sup> /gal (m <sup>2</sup> /L)
Duraprime WB	125 to 250 (3.1 to 6.1)	Duralkote 240, 1st coat	100 to 150 (2.5 to 3.7)
or		Duralkote 240, 2nd coat	100 to 150 (2.5 to 3.7)
Duraltex Clear	150 to 300 (3.7 to 7.4)	Eucothane, seal coat	300 to 500 (7.4 to 12.3)

**Note:** Coverage rates are approximate. Actual coverage depends on temperature, texture, and substrate porosity.

## DIRECTIONS FOR USE

**Surface Preparation:** The surface must be structurally sound, clean and free of grease, oil, curing compounds, soil, dust and other contaminants. See note in “Precautions/Limitations” section if coating is to be placed over old/existing epoxy or urethane coatings. New concrete and masonry must be at least 28 days old. Surface laitance must be removed. Concrete surfaces must be roughened and made absorptive, preferably by mechanical means, and then thoroughly cleaned of all dust and debris. If the surface was prepared by chemical means (acid etching), a water/baking soda or water/ammonia mixture, followed by a clean water rinse, must be used for cleaning, in order to neutralize the substrate. The Concrete Surface Profile (CSP) should be equal to CSP 2-4 in accordance with Guideline 310.2R-2013, published by the International Concrete Repair Institute (ICRI). Allow substrate to dry before coating application. Following surface preparation, the strength of the surface can be tested if quantitative results are required by project specifications. An elcometer or similar tensile pull tester may be used in accordance with ASTM C1583, and the tensile pull-off strength should be at least 250 psi (1.7 MPa).

Do not apply epoxy or urethane coatings if there is excessive moisture in the concrete or if the moisture vapor emission rate (MVER) is high. Before application of the coating, perform the “Visqueen test” (ASTM D4263) to check if there is moisture present. If moisture is found to be present during the “Visqueen test”, perform the “calcium chloride test” (ASTM F1869) as a follow-up to determine the MVER. Contact Euclid Chemical if results indicate a MVER greater than 3.0 lbs. per 1,000 square feet per 24 hours. After surface preparation and moisture testing, a test section application of the coating system is recommended to confirm good adhesion and compatibility of the coating with the surface, and also to confirm appearance and aesthetics.

When coating steel, all contamination should be removed and the steel surface prepared to a “near white” finish (SSPC SP10) using clean, dry blasting media.

**Mixing:** Mix DURALKOTE 240 using a low-speed drill and a mixing paddle. Pre-mix Part A and Part B separately for approximately 3 minutes each. If DURALKOTE 240 NEUTRAL BASE and a EUCLID UNIVERSAL COLOR PACK are being used, it takes 1 EUCLID UNIVERSAL COLOR PACK per 2 gal (7.6 L) unit. Add the EUCLID UNIVERSAL COLOR PACK into the Part B and mix slowly until the color is uniform. Combine Part A and Part B in a 1 to 1 ratio by volume, then mix thoroughly for 3 to 5 minutes. Scrape the bottom and sides of the containers at least once during mixing. Do not scrape bottom or sides of the container once mixing operations have ceased; doing so may result in unmixed resin or hardener being applied to the substrate. Unmixed resin or hardener will not cure properly. Do not aerate the material during mixing. To keep aeration to a minimum, the recommended mixing paddles are #P1 or #P2 as found in ICRI Guideline 320.5R-2014.

**Application:** See the “Epoxy & Urethane Coatings Application Guide” for installation means and methods. Note that any coverage rates or mixing ratios for epoxy or epoxy-aggregate combinations found in the “Epoxy & Urethane Coatings Application Guide” are approximations, and are for general reference only. For product-specific coverage rates and mixing ratios, refer to this technical data sheet.

Where an anti-skid surface is desired for DURALKOTE 240, broadcast approximately 0.25 to 0.50 lbs./ft.<sup>2</sup> (1.2 to 2.4 kg/m<sup>2</sup>) of clean, dry aggregate into the first coat. When the first coat has cured, sweep off excess aggregate. Proceed with the second coat of DURALKOTE 240 and the optional seal coat of EUCOTHANE listed in the “Coverage” section above.

## CLEAN-UP

Clean tools and application equipment immediately with acetone, xylene, or MEK. Clean spills or drips with the same solvents while still wet. Hardened DURALKOTE 240 will require mechanical abrasion for removal.

## PRECAUTIONS/LIMITATIONS

- Store DURALKOTE 240 indoors, protected from moisture, at temperatures between 50°F and 90°F (10°C and 32°C)
- Surface and ambient temperature during coating applications should be between 50°F and 90°F (10°C and 32°C)
- Material temperatures should be at least 50°F (10°C) and rising
- Do not apply DURALKOTE 240 if surface temperature is within 5°F (3°C) of the dew point in the work area
- Working time and cure time will decrease as the temperature increases, and will increase as the temperature decreases
- Do not thin DURALKOTE 240
- Do not apply DURALKOTE 240 to slabs on grade unless an uninterrupted vapor barrier has been installed under the slab
- Do not apply DURALKOTE 240 if the substrate is subject to excessive moisture vapor drive or hydrostatic pressure
- Although DURALKOTE 240 is chemically resistant, surface staining of the coating may occur after contact with some chemicals. Consider the use of a urethane topcoat such as EUCOTHANE for improved stain resistance.
- DURALKOTE 240 will discolor upon prolonged exposure to ultraviolet light and high-intensity artificial lighting. An aliphatic urethane topcoat such as EUCOTHANE can minimize these effects.
- Depending on the condition of the substrate, minor surface defects can appear in the coating when applied. Proper surface prep, patching of substrate imperfections, and priming will ensure a better overall finish.
- If coating over old/existing epoxy or urethane coatings, or if more than 24 hours elapses between coats: sand the previous coat, wipe clean, and proceed with coating operations. If old/existing coatings are peeling, flaking, etc., all unsound material must be removed prior to new coating applications.
- Application of a test area is recommended to confirm final appearance and texture of the system with the end user
- DURALKOTE 240 NEUTRAL BASE requires 1 EUCLID UNIVERSAL COLOR PACK per 2 gal (7.6 L) unit. Mix COLOR PACK into the Part B component.
- In all cases, consult the product Safety Data Sheet before use

Rev. 03.17

**WARRANTY:** The Euclid Chemical Company (“Euclid”) solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid’s installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid’s products for the Buyer’s intended purposes.