

# SikaQuick® VOH

Fast Setting, one component, cementitious vertical and overhead repair mortar with superior high build properties

<b>Description</b>	SikaQuick® VOH is a fast setting, one component, ready-to-use repair mortar for vertical and overhead applications using specialty cement blends.
<b>Where to Use</b>	<ul style="list-style-type: none"> <li>■ Fast repairs to overhead and vertical concrete and mortar surfaces on grade, above and below grade.</li> <li>■ As a repair material for building facades, parking structures, industrial plants, bridges, etc.</li> <li>■ As a fast setting repair material for new construction defects.</li> </ul>
<b>Advantages</b>	<ul style="list-style-type: none"> <li>■ Minimal time required between lifts.</li> <li>■ Fast finishing time</li> <li>■ Time/labor-saving material; application up to 3 inches on vertical surfaces in one layer</li> <li>■ Easy to use; just add water</li> <li>■ High bond strength ensures excellent adhesion</li> <li>■ High early and ultimate strength</li> <li>■ Increased freeze/thaw durability and resistance to deicing salts</li> <li>■ Suitable for exterior and interior applications.</li> <li>■ Not a vapor barrier</li> <li>■ Overhead thickness up to 2"</li> <li>■ Fiber reinforced and polymer modified</li> <li>■ Contains corrosion inhibitor</li> </ul>
<b>Coverage</b>	~.44 cu. ft.
<b>Packaging</b>	44 lb bag

**Typical Data (Material and curing conditions @ 73°F (23°C) and 50% R.H.)**

RESULTS MAY DIFFER BASED UPON STATISTICAL VARIATIONS DEPENDING UPON MIXING METHODS AND EQUIPMENT, TEMPERATURE, APPLICATION METHODS, TEST METHODS, ACTUAL SITE CONDITIONS AND CURING CONDITIONS. THIS DATA REFLECTS MATERIAL TESTED AT A MIXING RATIO OF 6.25 PINTS/UNIT.

<b>Shelf Life:</b>	One year in original, unopened bags.		
<b>Storage Conditions:</b>	Store dry at 40°-95°F (4°-35°C).		
<b>Product Conditioning:</b>	Condition material to 65°-75°F before using.		
<b>Color:</b>	Concrete gray.		
<b>Mixing Ratio:</b>	6 - 6.5 pints/unit		
<b>Density (Wet mix):</b>	~ 125 lbs. / cu. ft.		
<b>Application Time:</b>	Approximately 20 minutes.		
<b>Finishing Time:</b>	20-30 minutes		
<b>Lift Height:</b>	Max: 3"	Min: 1/8"	
<b>Time Between Lifts:</b>	After final set		
<b>Splitting Tensile Strength, psi (ASTM C-496)</b>		<b>1 day</b>	<b>7 days</b> <b>28 days</b>
		200	250      500
<b>Compressive Strength, psi (ASTM C-109):</b>	<b>3 hrs</b>	<b>1 day</b>	<b>7 days</b> <b>28 days</b>
	>2000	>3000	>4500      5500
<b>Flexural Strength, psi (ASTM C-293):</b>		<b>1 day</b>	<b>7 days</b> <b>28 days</b>
		400	600      1000
<b>Bond Strength*, psi (ASTM C-882 modified):</b>		<b>1 day</b>	<b>7 days</b> <b>28 days</b>
		1000	1600      2000
<b>Modulus of Elasticity, psi (ASTM C-469)</b>			<b>7 days</b>
			>2.2 x 10 <sup>6</sup>
<b>Rapid Chloride Permeability (ASTM C1202)</b>		Low Range	
<b>Bond Strength, psi - Direct Tensile (ICRI No. 210.3):</b>		Substrate failure >250	
<b>Shrinkage (50% R.H.) (ASTM C-157; ICRI protocol):</b>		<.05%	
<b>Initial Set, min. (ASTM C-266)</b>		20-25	
<b>Final Set, min. (ASTM C-266)</b>		30-40	

\*Mortar scrubbed into substrate

**PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://USA.SIKA.COM/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.**



<b>How to Use</b>	
<b>Surface Preparation</b>	<p><b>Concrete/Mortar:</b> Remove all deteriorated concrete, dirt, oil, grease, and all bond-inhibiting materials from surface. Preparation work should be done by high pressure water blast, scabber or other appropriate mechanical means to obtain an exposed aggregate surface profile of +/- 1/16 in. (CSP-5). After preparation, substrate strength should be verified prior to patch placement. Substrate should be saturated surface dry (SSD) with no standing water during application.</p> <p><b>Reinforcing Steel:</b> Steel reinforcement should be thoroughly prepared by mechanical cleaning to remove all traces of rust. Where corrosion has occurred due to the presence of chlorides, the steel should be high pressure washed with clean water after mechanical cleaning.</p>
<b>Priming:</b>	<p><b>Reinforcement Steel:</b> For priming of reinforcement steel use Sika® Armatec® 110 EpoCem (Consult Technical Data Sheet).</p> <p><b>Concrete Substrate:</b> A scrub coat of SikaQuick® VOH should be applied prior to placement of mortar. The repair mortar has to be applied into the wet scrub coat before it dries. The use of Sika® Armatec® 110 EpoCem as a bonding agent for concrete is not recommended.</p>
<b>Mixing</b>	<p>Wet down all tools and mixer to be used. Mix mechanically with a low-speed drill (400 - 600 rpm) and mixing paddle or mortar mixer. Mix to a uniform consistency, maximum 3 minutes. Manual mixing can be tolerated only for less than a full unit. Thorough mixing and proper proportioning of the powder and liquid is necessary. Inaccurate proportioning of the powder to liquid will result in a finished product that may not conform with stated properties.</p> <p><b>With water:</b> Start mixing with 6 pints of water per 44 lb. bag. Adjust the water dosage by a maximum amount of +/- 1/2 pint, if necessary, to achieve the desired consistency. Do not over-water. Over-watering may result in difficulty handling and/or not meeting stated property values.</p> <p><b>With Latex R:</b> Start mixing with 6 pints of SikaLatex® R per 44 lb. bag. Adjust the SikaLatex® R dosage by a maximum amount of +/- 1/2 pint, if necessary, to achieve the desired consistency.</p>
<b>Application</b>	<p>The mixed SikaQuick® VOH must be worked well into the prepared substrate, filling all pores and voids. Compact well. Force material against edge of repair working towards the center. Thoroughly compact the mortar around exposed reinforcement. After filling repair, consolidate, then screed. Finish with steel, magnesium, wood, plastic floats, or damp sponges, depending on the desired surface texture. Where multiple lifts are required, score top surface on each lift to produce a roughened substrate for next lift. Allow preceding lift to harden before applying fresh material. Saturate surface of the lift with clean water. If previous layers are over 6 hours old, mechanically prepare the substrate and dampen.</p>
<b>Tooling and Finishing</b>	<p>As per ACI recommendations for portland cement concrete, curing is required. Moist cure with wet burlap and polyethylene, a fine mist of water or a water based* compatible curing compound. Curing compounds adversely affect the adhesion of following lifts of mortar, leveling mortar or protective coatings. Moist curing should commence immediately after finishing. Protect freshly applied mortar from direct sunlight, wind, rain and frost.</p> <p>* Pretesting of curing compound is recommended.</p>
<b>Removal</b>	<p>Cured product must be removed mechanically.</p>
<b>Over Painting</b>	<p>Acrylic waterbased systems - 4 hrs Epoxy/PU based systems - 6 hrs Compatibility and adhesion testing is always recommended.</p>
<b>Limitations</b>	<ul style="list-style-type: none"> <li>■ Application thickness: Minimum: With water: 1/8 inch (3 mm). Maximum in one lift: 3 inches (75 mm) vertical, 2 inches (51 mm) overhead.</li> <li>■ Minimum ambient and surface temperatures 45°F (7°C) and rising at time of application.</li> <li>■ To control setting times, cold water should be used in hot weather and hot water used in cold weather.</li> <li>■ Do not use solvent based curing compounds. As with all cement based materials, avoid contact with aluminum to prevent adverse chemical reaction and possible product failure. Insulate potential areas of contact by coating aluminum bars, rails, posts etc. with an appropriate epoxy such as Sikadur® Hi-Mod 32.</li> <li>■ Remixing product after it begins to set is prohibited.</li> <li>■ Do not use Sika® Armatec® 110 EpoCem as a bonding agent with SikaQuick® VOH.</li> </ul>



**PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.**

# Construction

**PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.**

KEEP CONTAINER TIGHTLY CLOSED. KEEP OUT OF REACH OF CHILDREN. NOT FOR INTERNAL CONSUMPTION. FOR INDUSTRIAL USE ONLY. FOR PROFESSIONAL USE ONLY.

For further information and advice regarding transportation, handling, storage and disposal of chemical products, users should refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety related data. Read the current actual Safety Data Sheet before using the product. In case of emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Product Data Sheet, product label and Safety Data Sheet which are available online at <http://usa.sika.com/> or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Product Data Sheet, product label and Safety Data Sheet prior to product use.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS. SALE OF SIKA PRODUCTS ARE SUBJECT SIKA'S TERMS AND CONDITIONS OF SALE AVAILABLE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING 201-933-8800.

Visit our website at [usa.sika.com](http://usa.sika.com)

1-800-933-SIKA NATIONWIDE

**Regional Information and Sales Centers.** For the location of your nearest Sika sales office, contact your regional center.

**Sika Corporation**  
201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: 800-933-7452  
Fax: 201-933-6225

**Sika Canada Inc.**  
601 Delmar Avenue  
Pointe Claire  
Quebec H9R 4A9  
Phone: 514-697-2610  
Fax: 514-694-2792

**Sika Mexicana S.A. de C.V.**  
Carretera Libre Celaya Km. 8.5  
Fracc. Industrial Balvanera  
Corregidora, Queretaro  
C.P. 76920  
Phone: 52 442 2385800  
Fax: 52 442 2250537



Sika and SikaGrout are registered trademarks.  
Printed in Canada.